



Flame-retardant bedding compounds for XLPE insulation and HFFR sheathing.

■ Compound class

Bedding compound

■ Based on

TPE-O

■ Characteristics

Halogen-free flame retardant

■ Application examples: Insulation

2 XI 1	XLPE	acc. DIN / VDE 0207 part 22
2 YI 1 - 5	PE	acc. DIN / VDE 0207 part 2
9 YI 1	PP	acc. DIN / VDE 0207 part 7
3 GI 3	EPR	acc. DIN / VDE 0207 part 20

■ Application examples: Sheathing

HM 4 – 2	HFFR	acc. DIN / VDE 0207 part 24
2 YM 3	HDPE	acc. DIN / VDE 0207 part 3

■ Typical applications

Bedding compound for cables and wire with max. 90°C operating temperature at conductor.



Home



City



Industry

■ Features



For 2-step process (coilable)



Flame retardant



Halogen-free

PHYSICAL PROPERTIES

■ Physical properties	Unit	Typical value	Test method
Density*	g/cm ³	1,81	DIN EN ISO 1183-1A
Hardness*	Shore A	65	DIN ISO 7619-1
Mooney viscosity, ML (1+4) 100°C	MU	45	DIN 53 523

MECHANICAL PROPERTIES

■ Thermoplastic *	Unit	Typical value	Test method
Tensile strength	N/mm ²	1,5	IEC 811-1-1
Elongation at break	%	20	IEC 811-1-1

BURNING PROPERTIES *

■ Main burning properties	Unit	Typical value	Test method
LOI	%	67	ASTM D 2863 A
■ Acid gas emission	Unit	Typical value	Test method
pH (min.)	-	≥ 4,3	DIN VDE 0472- 813
Conductivity (max.)	μS cm-1	≤ 100	

* pressed plaques, 100°C / 5 min.

PROCESSING GUIDE

■ Extruder type

Standard extruders for elastomeric or thermoplastic processing

■ Screw configuration


Low compression screw with L/D of 12 to 25

■ Tooling

semi-compression or tube

■ Temperature profile extruder

The profile shown below may vary slightly depending on extruder type, head design & output.



■ Maximum mass temperature

110 – 115°C

■ Drying

Pre-drying of Melos FM Bedding Compounds is normally not necessary provided that the compound has been stored in the original sealed bags under cool (max. 30°C) and dry conditions.

STORAGE INFORMATION

■ Form & packaging

Pellets in sizes 5.5mm & 7.5mm
PE-bags (25 kg), Octabins (1.000-2.000 kg), BigBags (max. 1.250 kg)

■ Shelf life

1 year after production

Note: The information given in this datasheet is believed to be accurate and reliable. However, no warranty, express or implied, or guarantee is given as to the suitability, accuracy, reliability or completeness of the information. This information does not hold us liable for damages or penalties resulting from following our suggestions or recommendations.

0728 dat e*16.01.2017* SK